
(12) **UK Patent Application** (19) **GB** (11) **2 025 928 A**

(21) Application No **7923657**

(22) Date of filing **6 Jul 1979**

(23) Claims filed **6 Jul 1979**

(30) Priority data

(31) **53/083174**

(32) **8 Jul 1978**

(33) **Japan (JP)**

(43) Application published

30 Jan 1980

(51) **INT CL³**

C03C 3/10

C04B 31/06

(52) Domestic classification

C1M 101 134 140 141

144 150 157 159 171 214

242 AG

C3N 3A2C 3B3

(56) Documents cited

None

(58) Field of search

C1M

(71) Applicants

Nippon Sheet Glass Co.

Ltd., No. 8 4-chome,

Doshomachi, Higashi-ku,

Osaka, Japan

(72) Inventor

Makoto Kume

(74) Agents

J. A. Kemp & Co.

(54) **Alkali-resistant glass composition**

(57) An alkali-resistant glass composition consists essentially of

SiO_2 51.0 — 61.0 %

ZrO_2 18.0 — 24.0 %

CaO 0.8 — 5.0 %

BaO 1.5 — 13.0 %

Na_2O 8.0 — 17.0 %

K_2O 0 — 5.0 %


B_2O_3 0 — 3.0 %

Al_2O_3 0 — 3.0 %

all percentages being based on the weight of the glass composition. The glass composition can be used to provide glass fibers suitable for use as reinforcement for cementitious products.

GB2 025 928A

(1/1)

Fig. 1

SPECIFICATION

Alkali-resistant glass composition

- This invention relates to an alkali-resistant glass composition, and more specifically, to a novel alkali-resistant glass composition suitable for the production of alkali-resistant glass fibers used to reinforce cementitious products.
- Glass fibers are widely used as reinforcing materials for various plastics and cementitious materials because of their higher tensile strength and modulus of elasticity than organic fibers and other inorganic fibers. In particular, glass fiber-reinforced cements have been actively investigated in many fields to meet the recent requirement for cementitious products of lighter weight and higher strength.
- Cement is strongly alkaline because it contains Ca(OH)_2 which is derived from CaO as one component thereof and dissolved therein to saturation. Glass fibers used to reinforce cement are therefore exposed to a strong alkaline condition for long periods of time. When ordinary E-glass fibers are used as a reinforcing material for cement, they will be attacked by alkali to decrease greatly in strength, and fail to perform the function of reinforcing material. It is absolutely necessary for cement-reinforcing glass fibers to have alkali resistance.
- With such a background, many alkali-resistant glass fibers have recently been suggested for use in reinforcing cementitious products (see, for example, British Patent No. 1,290,528 and U.S. Patents Nos. 3,861,926, 4,066,465 and 3,861,927), and some of these glass fibers have already gained commercial acceptance.
- Cementitious products reinforced with such alkali-resistant glass fibers have better impact strength and flexural strength than those reinforced with other fibers, for example those reinforced with asbestos fibers (asbestos slate). However, the alkali-resistant glass fibers used heretofore do not have entirely satisfactory alkali resistance.
- In an attempt to improve this situation, it was suggested to coat the surface of glass fibers with an alkali-resistant material such as an alkali-resistant organic resin, a cationic emulsion of asphalt, a salt containing a zirconium ion, or a titanium salt (see for example, Japanese Laid-Open Patent Publications Nos. 148698/75, 40643/73, and 77692/75). This technique, however, has the disadvantage that the alkali-resisting effect of the coating is not permanent, and the coating process adds to the cost of production.
- It has generally been known that glass can be made alkali-resistant by incorporating zirconium oxide (ZrO_2) in a glass batch, and by increasing the content of ZrO_2 in the glass batch, the alkali resistance of the resulting glass increases. For example, Japanese Patent Publication No. 40126/74 discloses a glass composition for the production of alkali-resistant glass fibers, which comprises, by mole %, 62 to 72% of SiO_2 , 7 to 11% of ZrO_2 , 13 to 23% of R_2O , 1 to 10% of $\text{R}'\text{O}$, 0 to 4% of Al_2O_3 , 0 to 6% of B_2O_3 , 0 to 5% of Fe_2O_3 , 0 to 2% of CaF_2 and 0 to 4% of TiO_2 , in which R_2O represents Na_2O up to 2 mole % of which is replaceable by Li_2O and $\text{R}'\text{O}$ represents an alkaline earth metal oxide selected from Calcium oxide (CaO) zinc oxide (ZnO) and manganese oxide (MnO).
- U.S. Patent No. 4,066,465 and Japanese Laid-Open Patent Publication No. 127909/77, which were published after the publication of the aforesaid Japanese Patent Publication No. 40126/74, respectively disclose an alkali resistant glass composition comprising 53 to 63% by weight of SiO_2 , 21 to 23% by weight of ZrO_2 and 10 to 21% by weight of Na_2O as main ingredients, and an alkali-resistant glass composition comprising 61 to 69 mole % of SiO_2 , 11.5 to 13 mole % of ZrO_2 , 1 to 5 mole % of K_2O , 18 to 22 mole % of R_2O and 1 to 4 mole % of B_2O_3 (the amount of R_2O being the total amount of Na_2O and K_2O), the amount of $\text{ZrO}_2 + \text{B}_2\text{O}_3$ being not more than 15.5 mole %, and the mole ratio of ZrO_2 to K_2O being at least 2.6. The ZrO_2 contents of the alkali-resistant glass compositions described in these patent documents are slightly higher than that of the alkali-resistant composition described in the above-cited Japanese Patent Publication No. 40126/74.
- The alkali resistance of glass generally increases when the ZrO_2 content of the glass batch is increased. However, it is known that when the ZrO_2 content of the glass batch is increased beyond a certain limit, the devitrification tendency of the resulting glass abruptly becomes strong, and the liquidus temperature (a temperature at which crystals begin to precipitate when molten glass is slowly cooled) of glass abruptly rises. Thus, the operation of spinning the glass is difficult, and crystal grains are formed in the resulting glass fibers to reduce the strength of the fibers.
- Methods for avoiding the devitrification phenomenon or the rise in liquidus temperature have been investigated which involve properly controlling the types or contents of constituent ingredients of the glass batch other than ZrO_2 , or mixing a special ingredient (see, for example, U.S. Patent No. 3,973,974).
- In alkali-resistant glass fibers containing at least about 20% by weight of ZrO_2 now marketed, the occurrence of devitrification is prevented by maintaining the CaO content of the glass batch low and adding a third component such as K_2O or B_2O_3 .
- The present inventors examined the relation between the constituent proportions of glass and its alkali resistance in a four-component composition of SiO_2 — ZrO_2 — CaO — Na_2O , a basic conventional alkali-resistant glass composition containing ZrO_2 . The results are shown in Figure 1 attached to the

present application. In all glass compositions tested, the weight ratio of SiO_2 to $(\text{CaO} + \text{Na}_2\text{O})$ was maintained at 76:24, and the ZrO_2 content was adjusted to 17% by weight (curve I), 21% by weight (curve II), and 23% by weight (curve III), respectively based on the weight of the glass composition. The weight ratio of CaO to Na_2O was varied, and its relation to the alkali resistance of the resulting glass was determined. In Figure 1, the abscissa represents the weight ratio of CaO to Na_2O , and the ordinate, alkali resistance in terms of weight loss (%). A method for measuring the alkali resistance will be described in detail hereinbelow. Curve I refers to a glass composition having the ZrO_2 content taught by the above-cited Japanese Patent Publication No. 40126/74. Curves II and III refer to glass compositions having higher ZrO_2 contents. Figure 1 shows that when the $\text{CaO}/\text{Na}_2\text{O}$ weight ratio in the glass composition remains the same, the alkali resistance of the resulting glass increases with an increase in ZrO_2 content, and that when the ZrO_2 content of the glass batch remains the same, the alkali resistance of the resulting glass tends to increase with an increase in the $\text{CaO}/\text{Na}_2\text{O}$ ratio. It was noted that the tendency of glass to undergo devitrification is generally stronger with increasing $\text{CaO}/\text{Na}_2\text{O}$ ratios. Thus, in the case of the aforesaid commercially available alkali-resistant glass fibers having a ZrO_2 content of at least about 20% by weight, efforts are made to minimize the devitrification tendency of glass by reducing the $\text{CaO}/\text{Na}_2\text{O}$ ratio to nearly zero at the sacrifice of its alkali resistance.

It is seen from a comparison of curve I with curve II or III in Figure 1 that when the ZrO_2 content of the glass batch is high (curve II and III) but the $\text{CaO}/\text{Na}_2\text{O}$ ratio is near zero, the alkali resistance that can be attained is substantially the same as the highest alkali resistance which can be achieved when the ZrO_2 content is lower (curve I), namely the alkali resistance near the deflection point A of curve I.

In other words, even when the ZrO_2 content is increased greatly beyond 17% by weight, lowering of the $\text{CaO}/\text{Na}_2\text{O}$ ratio in an attempt to inhibit devitrification of glass cannot lead to the expected increase in alkali resistance. But rather, it brings about the serious disadvantage that the increase of the ZrO_2 content causes an increase in liquidus temperature, and makes the devitrification tendency stronger, resulting in reduced productivity.

The present inventors made investigations in order to provide a glass composition which can have an increased ZrO_2 content while maintaining the $\text{CaO}/\text{Na}_2\text{O}$ ratio at a high value, and which, therefore, has very high alkali resistance and markedly reduced devitrification tendency and does not appreciably increase in liquidus temperature, thus making it possible to produce glass with good productivity. As a result, they found that the aforesaid object can be achieved by incorporating a combination of a specified amount of BaO with CaO in a glass composition.

It is an object of this invention to provide a novel alkali-resistant glass composition having superior alkali resistance and much reduced devitrification tendency.

Another object of this invention is to provide an alkali-resistant glass composition having a high ZrO_2 content, superior alkali resistance, a low liquidus temperature, much reduced devitrification tendency, and good meltability (the property of the glass ingredients to be melted at relatively low temperatures within short periods of time and become a homogeneous glass).

Still another object of this invention is to provide alkali-resistant glass fibers produced from the above alkali-resistant glass composition which are suitable for reinforcing cementitious products.

Other objects and advantages of this invention will become apparent from the following description.

According to this invention, the objects and advantages are achieved by an alkali-resistant glass composition consisting essentially of

	SiO_2	51.0—61.0%	
45	ZrO_2	18.0—24.0%	45
	CaO	0.8— 5.0%	
	BaO	1.5—13.0%	
	Na_2O	8.0—17.0%	
	K_2O	0— 5.0%	
50	B_2O_3	0 — 3.0%	50
	Al_2O_3	0 — 3.0%	

all percentages being based on the weight of the glass composition.

The greatest characteristic of the alkali-resistant glass composition of this invention is the CaO and BaO are used together in the specified amounts. This makes it possible to greatly reduce the devitrification tendency of a glass composition having a fairly high ZrO_2 content, and to improve the

alkali resistance of the glass composition to a greater extent than in conventional alkali-resistant glasses. Furthermore, the liquidus temperature of the glass composition can be lowered, and the productivity of glass manufacture can be greatly increased.

The glass composition of this invention is described in more detail below. In the following description, the percentages used with regard to glass ingredients are based on the weight of the glass composition unless otherwise indicated.

In the glass composition of this invention, SiO_2 is a main basic ingredient and is included in an amount of 51.0 to 61.0%. If the SiO_2 content is less than 51.0%, glass tends to be devitrified. If it exceeds 61.0%, the meltability of the glass composition is reduced, and the spinning temperature of the glass rises to cause deformation of a platinum bushing, etc. The preferred SiO_2 content is 53.0 to 60.0%.

The content of ZrO_2 used to impart alkali resistance to the glass composition is as large as 18.0 to 24.0%. Preferably, it is incorporated in an amount of 19.0 to 22.0%.

CaO and BaO serve to reduce the devitrification tendency of glass which is caused by the incorporation of much ZrO_2 and to improve the alkali resistance of the resulting glass, CaO is used in an amount of 0.8 to 5.0%, preferably 1.0 to 4.0%, more preferably 1.5 to 3.0%. BaO is used in an amount of 1.5 to 13.0%, preferably 2.0 to 12.0%, more preferably 5.0 to 9.0%. When the amounts of CaO and BaO are less than the lower limits specified above, the use of such a large amount of ZrO_2 cannot fully improve the alkali resistance of glass. If these alkaline earth metal oxides are used in amounts larger than the specified upper limits, the interior of the resulting glass is liable to become opalescent owing to the formation of a crystal nucleus, and breakage tends to occur when forming the glass composition into fibers.

The total content of CaO and BaO has been found to greatly affect the alkali resistance of the glass. Desirably, the total amount of CaO and BaO is generally in the range of 5 to 15%, preferably 7 to 13%.

It has also been found that the mole ratio of $\text{BaO}/(\text{CaO}+\text{BaO})$ is also an important factor in reducing the devitrification of glass. Advantageously, the glass composition of this invention generally has a $\text{BaO}/(\text{CaO}+\text{BaO})$ mole ratio of from 0.2 to 0.8, preferably from 0.4 to 0.6.

Na_2O serves to improve the meltability of glass. If its amount is excessively small, the glass composition is difficult to melt, and if it is too large, the alkali resistance of the resulting glass tends to be reduced. Hence, the amount of Na_2O is 8.0 to 17.0%, preferably 9.0 to 16.0%.

K_2O and B_2O_3 are optional components in the present invention. If they are used in too large an amount, they will adversely affect the alkali resistance and devitrification tendency of glass. Accordingly, K_2O is used in an amount of up to 5.0%, and B_2O_3 in an amount of up to 3.0%. Preferably, these components should be substantially absent in the glass composition of this invention.

A small amount of Al_2O_3 exists unavoidably in glass as an impurity of a glass-forming batch. If its content increases too much, the devitrification tendency of glass increases. The content of Al_2O_3 is, therefore, 0 to 3.0%, preferably 0 to 2.0%.

A preferred alkali-resistant glass composition in accordance with this invention consists essentially of

	SiO_2	53.0—60.0%	
	ZrO_2	19.0—23.0%	
	Al_2O_3	0 — 2.0%	
	CaO	1.0— 4.0%	
45	BaO	2.0—12.0%	45
	Na_2O	9.0—16.0%	

all percentages being based on the weight of the glass composition.

The glass composition provided by this invention may also contain generally up to 5%, preferably up to 2%, of additives usually employed as minor components in the production of glass, for example CaF_2 , MgO , Li_2O , SnO_2 , ZnO , TiO_2 , La_2O_3 , SrO , MnO , and SO_3 , either singly or as a mixture.

CaF_2 serves to improve the meltability of the glass composition. If its content is too large, the alkali resistance of glass is reduced and its devitrification tendency increases. Hence, it is preferably used in an amount of generally 0 to 2.0% MgO , Li_2O , SnO_2 and TiO_2 , when used in too large amounts, would increase the tendency of glass to become opalescent. Generally, it is advantageous that MgO is used in an amount of 0 to 2%, Li_2O , 0 to 2%, SnO_2 , 0 to 5%, and TiO_2 , 0 to 3%. When ZnO is present in a large amount together with CaO in glass, the tendency of glass to become opalescent increases, and unmelted materials tend to occur in glass. Thus, ZnO is usually employed in an amount of up to 3%. If the amount of La_2O_3 is too large, the meltability and alkali resistance of glass are reduced, and therefore,

it is used generally in an amount of up to 5%. SO_3 may be used in an amount of generally 0 to 0.5% to improve the meltability of glass.

The glass composition of this invention may further comprise ordinary impurities and additives for facilitating the clarification of glass in a total amount of generally up to 2%, advantageously up to 1%.

5 Examples of such impurities and additives are Fe_2O_3 , CeO_2 , P_2O_5 , Cr_2O_3 , As_2O_3 , Sb_2O_3 , PbO , Bi_2O_3 , CdO , BeO , V_2O_5 , CoO , and CuO . 5

The glass composition of this invention has very high alkali resistance and much reduced devitrification tendency, and is especially suitable for production of glass fibers used to reinforce cementitious products.

10 Glass fibers can be produced from the glass composition in a customary manner, for example by holding a molten glass composition in a platinum bushing, and drawing it in a continuous filament form from tips provided at the bottom of the bushing. 10

The glass fibers obtained are especially useful for reinforcing cementitious products because they have very good alkali resistance, show only a very small weight loss in the measurement of alkali resistance to be described hereinbelow, and retain high strength over long periods of time.

15 15

The following Examples illustrate the present invention in more detail.

EXAMPLE 1

In each run, a glass composition having the constituents and proportions shown in Table 1 was placed in a platinum melter, and melted at 1500°C for 6 hours. The spinning temperature (T_w) and liquidus temperature (T_L) of the resulting glass were measured. 20

The spinning temperature (T_w), as is well known in general, denotes the temperature of the glass composition being drawn from the bushing at which temperature the viscosity of the glass is about 1000 poises. In view of the service life of the bushing, etc., the spinning temperature should desirably not exceed about 1350°C .

25 The liquidus temperature (T_L) is the temperature at which crystals begin to precipitate when a molten glass batch is gradually cooled. 25

When the difference between the spinning temperature and the liquidus temperature (i.e., $T_w - T_L$) is greater, the operability of fiber formation becomes better, and the tendency of "filament breakage" is less. If $T_w - T_L$ is at least 60°C , crystallization or the occurrence of foreign matter during the spinning operation can be avoided. 30

The alkali resistance of glass was measured by placing 3 g of a powder of the glass pulverized to 100 to 140 mesh in 150 ml of a 1N NaOH solution, holding it therein for 1.5 hours, and measuring the weight loss (%) of the glass powder. Smaller weight losses show better alkali resistance.

The results are shown in Table 1.

TABLE 1

Sample No.		Comparison				Invention										
		1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
Composition (wt. %)	SiO ₂	57.8	57.8	56.2	53.5	56.5	55.6	54.5	57.6	55.4	57.2	57.7	56.3	54.5	59.0	53.5
	Al ₂ O ₃	1.0	1.0	1.0	0.9	1.0	0.9	0.9	1.0	1.8	1.0	1.0	1.0	0.9	—	—
	ZrO ₂	23.0	23.0	22.4	21.3	22.5	22.1	21.7	20.6	22.4	20.3	20.6	20.0	21.7	21.0	19.3
	CaO	4.6	1.5	—	—	3.4	2.2	1.1	2.5	3.3	1.8	3.5	2.6	1.0	3.4	2.4
	BaO	—	—	4.1	11.6	3.1	6.0	8.9	3.4	3.0	5.0	3.2	7.1	8.8	2.7	11.7
	Na ₂ O	13.6	16.7	16.3	12.7	13.4	13.2	12.9	14.9	11.6	14.7	14.0	13.0	11.0	13.9	9.7
	K ₂ O	—	—	—	—	—	—	—	—	2.5	—	—	—	—	—	3.4
	B ₂ O ₃	—	—	—	—	—	—	—	—	—	—	—	—	2.1	—	—
BaO/(CaO + BaO) mole ratio		0	0	1.0	1.0	0.25	0.50	0.75	0.33	0.25	0.50	0.25	0.50	0.76	0.23	0.64
T _w		1340	1320	1335	1340	1315	1310	1325	1290	1330	1290	1320	1310	1320	1315	1290
T _L		1340	1300	1330	1320	1230	1225	1250	1200	1250	1215	1190	1190	1240	1230	1220
T _w - T _L		0	20	5	20	85	85	75	90	80	75	130	120	80	85	70
Alkali resistance (% weight loss)		0.17	0.23	0.14	0.20	0.15	0.11	0.12	0.14	0.13	0.14	0.14	0.15	0.13	0.14	0.13

Samples Nos. 1, 2, 3 and 4 are glass compositions shown as comparisons. All of these glass compositions have a high liquidus temperature (T_L), and are difficult to spin because $T_W - T_L$ is not at least 60°C.

Samples Nos. 5 to 15 are glass compositions of this invention.

5 The alkali resistances of conventional alkali-resistant glass compositions are generally within the range of 0.20 to 0.30%, whereas the glass compositions of this invention have excellent alkali resistance expressed by a weight loss of less than 0.20% (0.11 to 0.15%). 5

The spinning temperature of the glass compositions of this invention are lower than 1350°C, and $T_W - T_L$ is at least 60°C.

10 Samples Nos. 1 and 4 (comparisons), and Nos. 5, 6 and 7 (invention) commonly contain 65.9 mole % of SiO_2 , 0.6 mole % of Al_2O_3 , 12.8 mole % of ZrO_2 , 5.6 mole % of $(\text{CaO} + \text{BaO})$ and 15.1 mole % of Na_2O and the $\text{BaO}/(\text{CaO} + \text{BaO})$ mole ratio is set at 0, 0.25, 0.5, 0.75, 1.0, respectively in the order of the sample numbers given. When the CaO or BaO content is zero, $T_W - T_L$ is small, and the alkali resistance of the glass is unsatisfactory. It is clear however from the above table that when the aforesaid 15 mole ratio is 0.5, the $T_W - T_L$ value and the alkali resistance are best. 15

As stated hereinabove, the present invention has made it possible to fiberize the glass composition at a temperature which is industrially possible, and also to produce alkali-resistant glass having a very high level of alkali resistance.

EXAMPLE 2

20	SiO_2	56.3% by weight	20
	ZrO_2	20.1 "	
	CaO	3.0 "	
	BaO	8.2 "	
	Na_2O	12.1 "	
25	Al_2O_3	0.3 "	25

The above ingredients were placed in a platinum-rhodium alloy melter, and melted at 1500°C for 6 hours. The resulting glass had a spinning temperature (T_W) of 1330°C, and a liquidus temperature (T_L) of 1255°C. Accordingly, $T_W - T_L$ was 75°C. The alkali resistance value determined by the method described hereinabove was 0.14%.

30 The resulting glass was drawn by a bushing of platinum (80%)/rhodium (20%) alloy having an inside volume of 1300 ml and fifty tips, and taken up on bobbins at a take-up speed of 1200 m/min. 30

The tensile strength of the resulting glass fibers was measured in the following manner.

A strand, 20 cm long, composed of fifty glass fibers having a diameter of 13 to 15 microns was tested for tensile strength in cement. The strand was surrounded by ordinary portland cement mortar at 35 its center portion ranging over several centimeters, and the mortar was aged for one day at room temperature in the air. It was then held in water at 60°C for a predetermined period of time, and taken out. The tensile strength of the glass strand was then measured. 35

The glass strand in the present Example had a tensile strength of 150 kg/mm² which decreased to 117, 90, 78, 72, 70, 67, and 59 kg/mm² after it was held in water for 1, 3, 7, 14, 21, 28, and 56 days, 40 respectively. 40

For comparison, commercially available alkali-resistant glass fibers (SiO_2 62.4%, Al_2O_3 0.7%, ZrO_2 16.8%, CaO 5.5%, Na_2O 14.6%; spinning temperature, T_W , 1305°C; liquidus temperature, T_L , 1200°C; alkali resistance measured as above 0.23%) were tested for tensile strength in the same way as above. The untreated glass fiber strand had a tensile strength of 157 kg/mm², which decreased to 91, 74, 57, 45 55, 52, 51, and 41 kg/mm² after it was held in water for 1, 3, 7, 14, 21, 28, and 56 days respectively. 45

CLAIMS

1. An alkali-resistant glass composition consisting essentially of

	SiO ₂	51.0—61.0%	
	ZrO ₂	18.0—24.0%	
5	CaO	0.8— 5.0%	5
	BaO	1.5—13.0%	
	Na ₂ O	8.0—17.0%	
	K ₂ O	0— 5.0%	
	B ₂ O ₃	0— 3.0%	
10	Al ₂ O ₃	0— 3.0%	10

all percentages being based on the weight of the glass composition.

2. A glass composition according to claim 1 wherein the total amount of CaO and BaO is 5 to 15%, based on the weight of the glass composition.

3. A glass composition according to claim 1 or 2 wherein the mole ratio of BaO/(CaO+BaO) is 15 from 0.2 to 0.8. 15

4. An alkali-resistant glass composition according to claim 1, 2 or 3 which consists essentially of

	SiO ₂	53.0 — 60.0%	
	ZrO ₂	19.0—23.0%	
	CaO	1.0— 4.0%	
20	BaO	2.0—12.0%	20
	Na ₂ O	9.0—16.0%	
	Al ₂ O ₃	0 — 2.0%	

5. A glass composition according to claim 1 wherein the total amount of CaO and BaO is 7 to 13% based on the weight of the glass composition, and the mole ratio of BaO/(CaO+BaO) is from 0.4 to 0.6.

25 6. A glass composition according to claim 1 substantially as described by reference to Samples 5 to 15 of Example 1, or by reference to Example 2. 25

7. Alkaline-resistant glass fibers prepared from a glass composition as claimed in any one of the preceding claims.

8. A cementitious product reinforced with glass fibers as claimed in claim 7.